

			GR70	GR80	GR100	GR115	GR135	GR150	GR200	GR250 <sup>(1)</sup>
Density	ISO 845	kg/m <sup>3</sup>	70 <sup>(2)</sup>	80 <sup>(2)</sup>	100 <sup>(2)</sup>	115 <sup>(2)</sup>	135 <sup>(2)</sup>	150 <sup>(2)</sup>	200 <sup>(2)</sup>	250 <sup>(2)</sup>
Compression Strength	ISO 844	MPa	0,75	0,95	1,5	1,8	2,3	2,6	3,6	5,0
Compression Modulus	ISO 844	MPa	40	57	70	80	90	105	157	210
Shear Strength <sup>(3)</sup>	ISO 1922	MPa	0,5	0,55	0,75	0,9	1,2	1,4	1,8	1,9
Shear Modulus <sup>(3)</sup>	ISO 1922	MPa	13	15	20	25	35	40	50	70
Shear Strain <sup>(3)</sup>	ISO 1922	%	15	15	10	10	7	7	5	3
Tensile Strength	ASTM C 297	MPa	1,8	2,1	2,4	2,7	3,0	3,4	4,4	4,5
Tensile Modulus	ASTM C 297	MPa	66	75	105	120	140	190	230	240
Thermal Conductivity	at 23 °C	W/mK	0,034	0,034	0,034	0,034	0,037	0,041	0,043	0,047

**Fire, Smoke & Toxicity<sup>(4)</sup>**

B2	EN ISO 11925:2	tbd	B2 <sup>(5)</sup>	B2 <sup>(5)</sup>	B2 <sup>(5)</sup>	B2 <sup>(5)</sup>	B2 <sup>(5)</sup>	B2 <sup>(5)</sup>	tbd
----	----------------	-----	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	-----

**Tolerances**
**Length    Width    Diagonal    Thickness**

Dimensions (mm) <sup>(6)</sup>	2.448	1.008	<sup>(7)</sup>	GR70-GR80: 10–150mm GR100-GR250: 5-150mm
Tolerances (mm) at room temperature	+/- 5	+/- 5	≤ 4	≤ 100mm: GR70-GR250 +/- 0,5 ≥ 100mm: GR70-GR250 +/- 1

<sup>(1)</sup> Preliminary data (indication based on a limited number of tests).

<sup>(2)</sup> Tolerances: +/- 5 kg/m<sup>3</sup>

<sup>(3)</sup> // direction (parallel to the weld)

<sup>(4)</sup> For detailed test results and certificates please contact us.

<sup>(5)</sup> As of 50mm.

<sup>(6)</sup> Standard dimension. Further dimensions on special request.

<sup>(7)</sup> Depending on length and width combination.

All values are average production figures. Minimum values on request.

ArmaFORM<sup>®</sup> PET products are CFC / HFC free.

Customs tariff code: 39.21.19.00



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of these products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as technical service, and the data and information are subject to change without notice.

**Armacell Benelux S.A.**

Rue des Trois Entités 9 - B-4890 Thimister-Clermont

Tel.: +32 (0) 87 32 50 70 - Fax: +32 (0) 87 32 50 71

info.armaform@armacell.com - www.armacell-foam-cores.com

Copyright: Armacell Benelux SA, subject to changes - 200-004/07-0611-(GB)-WW

Document No.: DSWnm20151015, Rev00

